

**Característica / Characteristic /  
Caractéristique**
**Requerimentos / Requirements /  
Exigences**
**Resultado / Result / Résultat**

Humidade / Humidity / Humidité	Declaração / Declaration / Déclaration	0,22%
Empeno / Cupping / Gauchissement	Declaração / Declaration / Déclaration	0,05mm
Densidade / Density / Densité	Declaração / Declaration / Déclaration	1469 Kg/m <sup>3</sup>
Escorregamento / Slipperiness / Antidérapante		Class 3
Resistencia Impacto / Impact Resistance / Résistance aux Chocs	≤ 0,5mm	Max 0,12mm
Propriedades à Flexão / Flexural Properties / Propriétés Mécaniques	F <sup>l</sup> Max >3300N (Média / Mean / Moyenne)	6650
	F <sup>l</sup> Max >3000N (Individual / Individual / Individuelles)	6729,66
	Deflecção com carga 500N (média) / Deflection under load 500N (mean) / Fléchissement sous charge 500N (moyenne) ≤2mm	0,729
	Deflecção com carga 500N (individual) / Deflection under load 500N (individual) / Fléchissement sous charge 500N(individuelles) ≤2,5mm	0,722
Inchamento e absorção de água / Swelling and Water Absorption / Gonflement et Absorption d'eau	Absorção (média) / Absorption (mean) / Absorption (moyenne)	
	≤ 4% (espessura / thickness / épaisseur)	1,08%
	≤ 0,8% (largura / width / largeur)	0,21%
	≤ 0,4% (comprimento / length / longueur)	0,08%
	Absorção (individual) / Absorption (individual) / Absorption (individuelles) - MAX	
	≤ 5% (espessura / thickness / épaisseur)	2,11%
	≤ 1,2% (largura / width / largeur)	0,15%
Imersão em Água Quente / Boiling Test / Essai Bouillante	≤ 0,6% (comprimento / length / longueur)	0,12%
	Media Absorção / Mean Absorption / Absorption Moyenne - 7% w/w	1,13%
	Maximo individual / Individual Maximum / Maximum Individuelle - 9% w/w	1,11%
	Media Absorção / Mean Absorption / Absorption Moyenne ≤7% w/w	0,87%
	Maximo individual / Individual Maximum / Maximum Individuelle ≤9% w/w	1,20%
Composição / Composition / Composition	40% / 50% Madeira / Wood / Bois	
	1,5% SMP	
	40% / 50% Polimero / Polymer / Polymère	
	10% Outros / Others / Autres	
Vicat	Declaração / Declaration / Déclaration	85,2°C
HDT	Declaração / Declaration / Déclaration	74°C
Coef. Expansão Termica / Coef. Thermal Expansion / Coef. de Dilatation Thermique	≤ 50x10 <sup>-6</sup> K	2,79x10 <sup>-5</sup> mm/mm°C
Resistência ao Envelhecimento Artificial / Resistance to Artificial Weathering / Vieillessement Artificiel	Declaração / Declaration / Déclaration	ΔL < 2
Marcação / Mark / Mark	Declaração / Declaration / Déclaration	<b>EN15534-4 PVC W 50 UC3</b>

Declaração do fabricante / Manufacturer's Declaration / Déclaration du fabricant