

**Característica / Characteristic / Caractéristique**
**Requerimentos / Requirements / Exigences**
**Resultado / Result / Résultat**

Humidade / Humidity / Humidité	Declaração / Declaration / Déclaration	0,90%
Empeno / Cupping / Gauchissement	Declaração / Declaration / Déclaration	2mm/lm
Densidade / Density / Densité	Declaração / Declaration / Déclaration	1470 Kg/m <sup>3</sup>
Escorregamento / Slipperiness / Antidérapante	≥ 36	Média / Mean / Moyenne: 52 Mínimo / Minimum / Minimum: 49
Resistencia Impacto / Impact Resistance / Résistance aux Chocs	≤ 0,5mm	Max 0,1mm
	Deflexão com carga 250N (média) / Deflection under load 250N (mean) / Fléchissement sous charge 250N (moyenne) ≤5mm	3.1
	Absorção (média) / Absorption (mean) / Absorption (moyenne)	
	≤ 10% (espessura / thickness / épaisseur)	3.0%
	≤ 1,5% (largura / width / largeur)	0,50%
	≤ 0,6% (comprimento / length / longueur)	0,30%
	Absorção (individual) / Absorption (individual) / Absorption (individuelles) - MAX	
	≤ 12% (espessura / thickness / épaisseur)	2,81%
	≤ 2% (largura / width / largeur)	0,25%
	≤ 1.2% (comprimento / length / longueur)	0,13%
	Media Absorção / Mean Absorption / Absorption Moyenne - 8% w/w	4,00%
	Maximo individual / Individual Maximum / Maximum Individuelle - 10% w/w	4.7%
	Media Absorção / Mean Absorption / Absorption Moyenne ≤7% w/w	2.8%
	Maximo individual / Individual Maximum / Maximum Individuelle ≤9% w/w	3.7%
		40% / 60% Madeira / Wood / Bois 40% / 60% Polímero / Polymer / Polymère 10% Outros / Others / Autres
Composição / Composition / Composition		
Vicat	Declaração / Declaration / Déclaration	85,2°C
HDT	Declaração / Declaration / Déclaration	74°C
Marcação / Mark / Mark	Declaração / Declaration / Déclaration	<b>EN15534-4 PVC W 50 UC3</b>

Declaração do fabricante / Manufacturer's Declaration / Déclaration du fabricant